

		WEIGHT PER Sq Ft	SIZE TOLERANCE		STRUCTURAL				SURFACE	THERMAL HYGROMETRIC			LIGHT	CHEMICAL		SAFETY				
		lbm / (thickness)	Dimension	Thickness	Water Absorption	Breaking Strength	Modulus of Rupture	Breaking Load Class	Abrasion Resistance	Linear Thermal-Expansion	Thermal Shock Resistance	Frost Resistance	Color Resistance to Light Exposure	Resistance to Chemicals (Acids, Bases and Salts)	Resistance to Stains	Dynamic Coefficient of Friction	Dry Static Coefficient of Friction	Wet Static Coefficient of Friction	Skid Resistance	
INTERNATIONAL STANDARD ESTABLISHED LIMITS			ISO 10545-2	ISO 10545-2	ISO 10545-3	ISO 10545-4	ISO 10545-4	EN 1339	ISO 10545-6	ISO 10545-8	ISO 10545-9	ISO 10545-12	DIN 51094	ISO 10545-13	ISO 10545-14	BCRA	ASTM C1028		DIN 51130	DIN 51097
			+/- 0.6%	+/- 5%	≤ 0.5%	≥ 1300 N	≥ 35 N/mm ²	Value Declared	≤ 175mm ³	Value Declared	Test Passed	Test Passed	No noticeable color modifications	UB Minimum	≥ 3	> 0.4	> 0.6	> 0.6	Value Declared	
TECHNIFIRMA™	Chimney Sweep	10.14 (0.79")	+/- 0.08"	+/- 0.02"	< 0.1%	≥ 13000 N	≥ 50 N/mm ²	U11 / T11	≤ 145mm ³	< 6.6x10 ⁻⁶ °C ⁻¹	Guaranteed	Guaranteed	No noticeable color modifications	UA ULA UHA Guaranteed	Guaranteed	0.91	0.97	0.78	R11	A+B+C
	Flint																			
	Grey Goose																			
	Mrs Char																			
	Muddled Crow																			
Riverdance																				